



— Mukavva ve Kağıt Ürünleri San. Tic. A.Ş. —

İkitelli O.S.B., Hürriyet Cad.
Saraçlar Sitesi, 14. Blok No:4/1
34490 Başakşehir / İstanbul

Tel : +90 212 485 4575 (pbx)
Fax : +90 212 485 4578
E-mail : info@sahinlerkagit.com.tr

ÖZELLİK Property	BİRİM Unit	KRAFT - Tipik Değerler Kraft Typical Values					Test Yöntemi Test Method	
		60 g/m ²	70 g/m ²	80 g/m ²	90 g/m ²	100 g/m ²		
GRAMAJ Grammage	g/m ²	60	70	80	90	100	ISO 536	
RUTUBET Moisture	%	6,5	6,5	6,5	6,5	6,5	ISO 287	
KOPMA MUKAVEMETİ Tensile Strength	kN/m	MD	4,7	5,4	6,2	7,0	7,8	ISO 1924-3
		CD	2,8	3,1	3,6	4,0	4,5	
UZAMA Stretch	%	MD	2	2	2	2	2	ISO 1924-3
		CD	6,5	6,5	6,5	6,5	6,5	
TEA Tensile Energy Absorption	J/m ²	MD	*	*	*	*	*	ISO 1924-3
		CD	*	*	*	*	*	
YIRTIK MUKAVEMETİ Tearing Strength	gf	MD	80	80	90	100	110	ISO 1974
		CD	85	85	100	115	120	
PATLAMA MUKAVEMETİ Bursting Strength	kg/cm ²	3,0	3,0	3,5	4,0	4,5	ISO 2758	
TUTKALLAMA Cobb60	g/m ²	30	30	30	30	30	ISO 535	
POROZİTE Porosity	s (Gurley)	25	25	25	25	25	ISO 5636-5	